

Aggregate Source Inventory Database



PIT NAME				06-0008CA	
Glancy Quarry - Omer					
DEPOSIT TYPE		ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED	
Carbonate Stone Quarry		1950		ACTIVE	
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
L.A. ABRASION (MTM 102)	A	21AA	31	04/25/2022	LA Abrasion results expire 5 years from reported date for this source
	B				
	C				
	D				
	E				
	F				
FREEZE-THAW TESTING (MTM 113, 114, 115)	Expansion				<i>The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid for 17 series gradations only</i>
	Crush				
	SG (OD)				
	Deleterious				
A.W.I. (MTM 112)	Wear Track Value		335	3/11/2018	Wear Track results expire 5 years from reported date
ADDRESS			LAST PRODUCER ON RECORD		
111 North Walker Road, Twining, MI 48766			R. E. Glancy/Lee Schunk		

Revised: Friday, February 24, 2023

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control

06-008 Historical