## **Aggregate Source Inventory Database**



				Michigan Department of Transportation	
PIT NAME					21-0095CA
Brayak Quarry					21-0095CA
DEPOSIT TYPE			ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED
Carbonate Stone Quarry			1992		ACTIVE
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
	Α				
L.A. ABRASION (MTM 102)	В	6AA	22	3/24/2021	LA Abrasion results expire 5 years from reported date for this source
	С				
	D				
	E				
	F				
FREEZE-THAW TESTING (MTM 113, 114, 115)	Expansion		0.027	6/3/2021	6AA tested, expires 6/2/2026
	Crush		100		The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid
	SG (OD)		2.70		for 17 series gradations only
	Deletrious		soft 1.0		%, sum of soft and chert 1.0%
A.W.I. (MTM 112)	Wear Track Value		244	1/9/2019	Wear Track results expire 5 years from reported date
ADDRESS		LAST PRODUCER ON RECORD			

8167 N.3 Lane, Gladstone, MI 49837

Bichler Concrete & Gravel

Revised: Tuesday, February 28, 2023

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control