## Aggregate Source Inventory Database



Aggregate coarse inventory Batabase					Michigan Department of Transportation
	ME			24 040556	
Duerson					21-0105SG
DEPOSIT TYPE			ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED
Sand & Gravel Quarry			2016		ACTIVE
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
	Α				
L.A. ABRASION (MTM 102)	В	НМА	36	7/29/2020	LA Abrasion results expire 5 years from reported date for this source
	С				
	D				
	E				
	F				
FREEZE-THAW	Expansion		0.041	11/2/2020	6A tested, expires 11/1/2025
TESTING (MTM 113, 114, 115)	Crush		86%		The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid for
	SG (OD)		2.61		17 series gradations only
	Deletrious		(clay iron 0.2%, sum of soft and chert 2.3%)		
A.W.I. (MTM 112)	Petrographic AWI				Contact Aggregate Quality
ADDRESS				LAST PRODUCER ON RECORD	

Revised: Wednesday, March 1, 2023

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control

Quarrystone Inc

v.25 Road, Rapid River, MI 49878