

Aggregate Source Inventory Database



PIT NAME				<h1>32-0004CA</h1>	
Wallace Stone					
DEPOSIT TYPE		ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED	
Carbonate Quarry		1929		ACTIVE	
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
L.A. ABRASION (MTM 102)	A				LA Abrasion results expire 5 years from reported date for this source
	B	6AA	32	9/15/2021	
	C				
	D				
	E				
	F				
FREEZE-THAW TESTING (MTM 113, 114, 115)	Expansion		0.045	7/11/2019	6AA tested, expires 7/9/2024 <i>The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid for 17 series gradations only</i>
	Crush		100		
	SG (OD)		2.59		
	Deletrious				
A.W.I. (MTM 112)	Wear Track Value		346	1/31/2023	Wear Track results expire 5 years from reported date
ADDRESS			LAST PRODUCER ON RECORD		
180 Bay Port Road, Bay Port, MI 48720			E.C. Levy - Burroughs Division		

Revised: Thursday, March 2, 2023

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control

32-004 Historical