## Aggregate Source Inventory Database



Michigan Department of Transportation					
PIT NAME					36-0075SG
V	S Oss			30-007300	
DEPOSIT TYPE			ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED
Sand & Gravel Quarry			2011		ACTIVE
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
	Α				
L.A. ABRASION (MTM 102)  FREEZE-THAW TESTING (MTM 113, 114, 115)	В	6A	20	8/26/2020	LA Abrasion results expire 5 years from reported date for this source
	С				
	D				
	Е				
	F				
	Expansion		0.003		6AA tested, expires 6/8/2026 The 6 series for FT is the standard and covers
	Crush		93	6/9/2021	ALL gradations, while the 17 series result is valid for 17 series gradations only
	SG (OD)		2.73		
	Deleterious		as tested (clay iron 0.9%, sum of soft and chert 4.8%)		
A.W.I. (MTM 112)	Petrographic AWI				Contact Aggregate Quality
ADDRESS		LAST PRODUCER ON RECORD			

**Huhtala Construction** 

Revised: Wednesday, July 26, 2023

36-075 Historical

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control