## **Aggregate Source Inventory Database**



					Michigan Department of Transportation
PIT NAME					40 00CEC A
Cedarville					49-0065CA
DEPOSIT TYPE			ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED
Carbonate Stone Quarry			1955		ACTIVE
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
	Α				
L.A. ABRASION (MTM 102)	В	6AA	28	1/21/2022	LA Abrasion results expire 5 years from reported date for this source
	С				
	D				
	Е				
	F				
FREEZE-THAW TESTING	Expansion		0.003	6/9/2022	6AA tested, expires 6/8/2027
	Crush		100		The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid
(MTM 113, 114, 115)	SG (OD)		2.78		for 17 series gradations only
	Deletrious		as tested (Deleterious 0.0%)		
A.W.I. (MTM 112)	Wear Track Value		182	6/6/2023	Results expires 5 years from posted date
ADDRESS LAST PRODUCER ON RECO					

5085 M-134, Clark Township, MI 49719

Carmeuse Lime And Stone

Revised: Wednesday, June 7, 2023

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control