## **Aggregate Source Inventory Database**



					Michigan Department of Transportation
PIT NAME					E0 0002CA
	Lake			58-0003CA	
DEPOSIT TYPE			ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED
Carbonate Stone Quarry			1953		ACTIVE
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
	Α				
L.A. ABRASION (MTM 102)	В	6A	25	12/19/2019	LA Abrasion results expire 5 years from reported date for this source
	С				
	D				
	Е				
	F				
FREEZE-THAW TESTING (MTM 113, 114, 115)	Expansion		0.010	12/9/2020	6A tested, expires 12/8/2025
	Crush		100		The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid for 17 series gradations only
	SG (OD)		2.65		
	17 Se	ries	0.035	9/6/2018	Crush: 100%
	Deletrious		as tested (soft 0.3%		o, chert 0.3%)
A.W.I. (MTM 112)	Wear Track Value		216	8/15/2017	Wear Track results extended until current testing is complete
ADDRESS			LAST PRODUCER ON RECORD		

approx 7651 Whiteford Road, Ottawa Lake, MI 49267

Stoneco - East

Revised: Tuesday, March 7, 2023

**58-003 Historical** 

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control