Aggregate Source Inventory Database



					Michigan Department of Transportation	
PIT NAME					E0 0002CA	
Ot	ke-St	one Co		58-0003CA		
DEPOSIT TYPE			ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED	
Carbonate Stone Quarry			1953		ACTIVE	
AGGREGATE QUALITY TESTING RESULTS						
Test	Grade	Material	Result	Date	NOTES	
	Α					
L.A. ABRASION (MTM 102)	В	34CS	27	05/01/2024	LA Abrasion results expire 5 years from reported date for this source	
	С					
	D					
	E					
	F					
FREEZE-THAW TESTING (MTM 113, 114, 115)	Expansion		0.010	12/9/2020	6A tested, expires 12/8/2025	
	Crush		100		The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid for 17 series gradations only	
	SG (OD)		2.65			
17 Series		ries	0.035	9/6/2018	Crush: 100%	
	Deletrious		as tested (soft 0.3%		o, chert 0.3%)	
A.W.I. (MTM 112)	Wear Track Value		216	8/15/2017	Wear Track results extended until current testing is complete	
ADDRESS				LAST PRODUCER ON RECORD		

approx 7651 Whiteford Road, Ottawa Lake, MI 49267

Stoneco

Revised: Wednesday, May 1, 2024

58-003 Historical

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control