Aggregate Source Inventory Database						
PIT NAME					58-0006CA	
	im			30-000CA		
DEPOSIT TYPE			ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED	
Carbonate Quarry			1959		ACTIVE	
AGGREGATE QUALITY TESTING RESULTS						
Test	Grade	Material	Result	Date	NOTES	
L.A. ABRASION (MTM 102)	A					
	В	6AA	45	01/31/2024	LA Abrasion results expire 5 years from reported date for this source	
	С					
	D					
	E					
	F					
FREEZE-THAW TESTING (MTM 113, 114, 115)	Expansion		0.030	3/9/2022	6AA tested, expires 3/8/2027	
	Crush		99		The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid for 17 series gradations only	
	SG (OD)		2.52			
	Deleterious		as tested (soft 0.6%, chert 0.3% -sum of soft and chert 0.9%)			
A.W.I. (MTM 112)	Wear Track Value		266	8/15/2017	Results valid until updated testing is finalized	
ADDRES				LAST PRODUCER ON RECORD		
15215 Day Road	48131			Holcim		

Revised: Wednesday, January 31, 2023

58-006 Historical

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control