Aggregate Source Inventory Database					<b>CALDOT</b> Michigan Department of Transportation
PIT NAME					
Newport Quarry					58-0011CA
DEPOSIT TYPE			ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED
Carbonate Quarry			1993		ACTIVE
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
L.A. ABRASION (MTM 102)	Α				LA Abrasion results expire 5 years from reported date for this source
	В	6 Series	30	02/16/2024	
	В	17A	31	02/16/2024	
	D				
FREEZE-THAW TESTING (MTM 113, 114, 115)	Expansion		0.105	4/9/2018	6AA tested, expires 11/1/2025
	Crush		95		24hr soak of 2.63% as tested during FT
	SG (OD)		2.53		The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid for 17 series gradations only
	Expansion		0.077*	01/25/2019	
	Crush		100*		*17 Series Tested, expires 01/24/2024
	SG (OD)		2.57*		*24hr soak of 2.88% as tested during FT
A.W.I. (MTM 112)	) Wear Track Value		254	6/3/2019	Wear Track results expire 5 years from reported date
ADDRES				LAST PRODUCER ON RECORD	
7250 Reaume Road	l 48166			Stoneco- East	
Povisod: Friday, February 16, 2023					

Revised: Friday, February 16, 2023

**58-011 Historical** 

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control