## **Aggregate Source Inventory Database**



|  |                  |                         |                        |            | Michigan Department of Transportation  |
|--|------------------|-------------------------|------------------------|------------|--|
| PIT NAME   |                  |                         |                        |            | 58-0013CA  |
| Sylvania Minerals  |                  |                         |                        |            | 30-00 13CA   |
| DEPOSIT TYPE   |                  |                         | ADDED TO DATABASE      |            | STATUS: INACTIVE/ACTIVE/URBANIZED  |
| Carbonate Stone Quarry   |                  |                         | 1998                   |            | ACTIVE   |
| AGGREGATE QUALITY TESTING RESULTS                                |                  |                         |                        |            |  |
| Test   | Grade            | Material                | Result                 | Date       | NOTES  |
|  | Α                | 4G                      | 36                     | 05/27/2022 |  |
| L.A. ABRASION (MTM 102)  FREEZE-THAW TESTING (MTM 113, 114, 115) | В                | 6AA                     | 30                     | 09/09/2019 | LA Abrasion results expire 5 years from reported date for this source                              |
|  | С                | НМА                     | 38                     | 09/28/2023 |  |
|  | D                |                         |                        |            |  |
|  | Е                |                         |                        |            |  |
|  | F                |                         |                        |            |  |
|  | Expansion        |                         | 0.136                  |            | 6AA tested, expires 1/12/2025  |
|  | Crush            |                         | 100                    | 1/14/2020  | The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid |
|  | SG (OD)          |                         | 2.59                   |            | for 17 series gradations only  |
|  | Deletrious       |                         | as tested (chert 4.0%) |            |  |
| A.W.I.<br>(MTM 112)  | Wear Track Value |                         | 197                    | 1/31/2023  | Wear Track results expire 5 years from reported date   |
| ADDRESS  |                  | LAST PRODUCER ON RECORD |                        |            |  |

5699 Ready Road, South Rockwood, MI 48179

Great Lakes Aggregate Co.

Revised: Thursday, September 28, 2023

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control