Aggregate Source Inventory Database					CALDOT Michigan Department of Transportation
PIT NAME					02 000100
Ardmore Quarry					92-0001CA
DEPOSIT TYPE			ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED
Carbonate Stone Quarry			1964		ACTIVE
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
L.A. ABRASION (MTM 102)	Α				LA Abrasion results expire 5 years from reported date for this source
	В		25	8/23/2022	
	С				
	D				
	E				
	F				
FREEZE-THAW TESTING (MTM 113, 114, 115)	Expansion		0.003	5/11/2023	6A tested, expires 5/10/2028
	Crush		100		The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid for 17 series gradations only
	SG (OD)		2.68		
	Deleterious				
A.W.I. (MTM 112)	Wear Track Value				No Data
ADDRESS					LAST PRODUCER ON RECORD
6100 Ardmore, Fort Wayne, IN 46809					Hanson Heidelburg Cement Group

Revised: Friday March 12, 2023

92-001 Historical

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control