## **Aggregate Source Inventory Database**



					Michigan Department of Transportation
PIT NAME					92-0007CA
Francesville Quarry					32-0001 CA
DEPOSIT TYPE			ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED
Carbonate Stone Quarry			1953		ACTIVE
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
	Α				
L.A. ABRASION (MTM 102)  FREEZE-THAW TESTING	В	6AA	31	1/27/2020	LA Abrasion results expire 5 years from reported date for this source
	С				
	D				
	E				
	F				
	Expansion		0.010		6AA tested, expires 11/1/2025
	Crush		100	11/2/2020	The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid
(MTM 113, 114, 115)	SG (OD)		2.70		for 17 series gradations only
	Deleterious				
A.W.I. (MTM 112)	Wear Track Value		193	1/31/2023	Wear Track results expire 5 years from reported date
ADDRESS		LAST PRODUCER ON RECORD			

14530 West 700 South, Francesville, IN 47976

U.S. Aggregates

Revised: Friday, March 10, 2023

92-007 Historical

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control