

Aggregate Source Inventory Database



PIT NAME				92-0030CA	
Pleasant Mills					
DEPOSIT TYPE		ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED	
Carbonate Quarry		1985		ACTIVE	
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
L.A. ABRASION (MTM 102)	A				LA Abrasion results expire 5 years from reported date for this source
	B	6A	32	1/23/2020	
	C				
	D				
	E				
	F				
FREEZE-THAW TESTING (MTM 113, 114, 115)	Expansion		0.009	12/2/2020	6A tested, expires 12/1/2025 <i>The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid for 17 series gradations only</i>
	Crush		100		
	SG (OD)		2.60		
	Deleterious				
A.W.I. (MTM 112)	Wear Track Value		197	6/6/2023	Result expires 5 years from the posted date
ADDRESS			LAST PRODUCER ON RECORD		
699 S 500 E, Decatur, IN 46733			Meshberger Bros. Stone Co		

Revised:

Wednesday, June 7, 2023

92-030 Historical

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control