

Aggregate Source Inventory Database



PIT NAME				92-0036SF	
South Shore Plant 2					
DEPOSIT TYPE		ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED	
Steel Furnace Slag		1994		ACTIVE	
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
L.A. ABRASION (MTM 102)	A				LA Abrasion results expire 5 years from reported date for this source
	B				
	C		12	3/6/2020	
	D				
	E				
	F				
A.W.I. (MTM 112)	Wear Track Value				No Data
ADDRESS			LAST PRODUCER ON RECORD		
1 North Buchanan Street, Gary, IN 47402			Beemsterboer		

Revised: Friday, March 10, 2023

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control

92-036 Historical