Aggregate Source Inventory Database

Concrete Industries is Permanently Closed



Concrete Industries

					Michigan Department of Transportation
PIT NAME Chase Quarry					94-0025
Chase Quarry					
DEPOSIT TYPE			ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED
Carbonate Quarry			1995		ACTIVE
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
L.A. ABRASION (MTM 102)	Α				LA Abrasion results expire 5 years from reported date for this source
	В	6AA	23	11/5/2020	
	С				
	D				
	Е				
	F				
FREEZE-THAW TESTING (MTM 113, 114, 115)	Expansion		0.000	8/12/2021	6AA tested, expires 8/11/2026
	Crush		99		The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid for 17 series gradations only
	SG (OD)		2.76		
	Deleterious		as tested (soft 1.2%, chert 0.2%)		
A.W.I. (MTM 112)	Wear Track Value		237	11/14/2022	Wear track result expires 5 years from reported date
ADDRESS LAST PRODUCER ON RECORD					

Revised: Wednesday, February 1, 2023

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control