

# Aggregate Source Inventory Database



|  |                         |                          |  |  |  |
|--|-------------------------|--------------------------|--|--|--|
| <b>PIT NAME</b>  |                         |                          |  | <b>94-0048IM</b>                         |  |
| <b>Evenson</b>   |                         |                          |  |  |  |
| <b>DEPOSIT TYPE</b>                                    |                         | <b>ADDED TO DATABASE</b> |  | <b>STATUS: INACTIVE/ACTIVE/URBANIZED</b> |  |
| Igneous/Metamorphic Quarry                             |                         | 2012                     |  | ACTIVE                                   |  |
| <b>AGGREGATE QUALITY TESTING RESULTS</b>               |                         |                          |  |  |  |
| <b>Test</b>  | <b>Grade</b>            | <b>Material</b>          | <b>Result</b>  | <b>Date</b>                              | <b>NOTES</b>   |
| <b>L.A. ABRASION<br/>(MTM 102)</b>                     | <b>A</b>                |                          |  |  | LA Abrasion results expire 5 years from reported date for this source  |
|  | <b>B</b>                |                          | <b>35</b>  | 9/15/2022                                |  |
|  | <b>C</b>                |                          |  |  |  |
|  | <b>D</b>                |                          |  |  |  |
|  | <b>E</b>                |                          |  |  |  |
|  | <b>F</b>                |                          |  |  |  |
| <b>FREEZE-THAW<br/>TESTING<br/>(MTM 113, 114, 115)</b> | <b>Expansion</b>        |                          | <b>0.002</b>   | 5/9/2023                                 | 6AA tested, expires 5/8/2028<br>The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is valid for 17 series gradations only |
|  | <b>Crush</b>            |                          | <b>86</b>  |  |  |
|  | <b>SG (OD)</b>          |                          | <b>2.79</b>  |  |  |
|  | <b>Deleterious</b>      |                          | as tested (soft 0.3%, chert 1.1% - sum of Deleterious 1.4% ) |  |  |
| <b>A.W.I.<br/>(MTM 112)</b>                            | <b>Wear Track Value</b> |                          |  |  | No Data  |
| <b>ADDRESS</b>   |                         |                          | <b>LAST PRODUCER ON RECORD</b>                               |  |  |
| 15500 County Road C, Valders, WI 54245                 |                         |                          | Evenson Construction   |  |  |

Revised: Thursday, May 11, 2023

## **94-048 Historical**

**NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control**