

Aggregate Source Inventory Database



PIT NAME				95-0006SF	
Algoma Steel Corp. Limited					
DEPOSIT TYPE		ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED	
Steel Furnace Slag		1987		ACTIVE	
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
L.A. ABRASION (MTM 102)	A				LA Abrasion results expire 5 years from reported date for this source
	B				
	C	29A	37	4/13/2022	
	D	HMA	29	2/9/2022	
	E	34CS	37	04/20/2022	
	F				
A.W.I. (MTM 112)	Wear Track Value		375	4/22/2016	Results valid until updated testing is finalized
ADDRESS			LAST PRODUCER ON RECORD		
105 West Street, Sault Ste. Marie, ON, Canada			Inter-Ontario Equipment Rental & Repair ULC		

Revised: Tuesday, April 25, 2023

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control

95-006 Historical