Aggregate Source Inventory Database



					Michigan Department of Transportation
PIT NAME Maple Ridge					95-0013SG
DEPOSIT TY		ADDED TO DATABASE		STATUS: INACTIVE/ACTIVE/URBANIZED	
Sand & Gravel Quarry			1987		ACTIVE
AGGREGATE QUALITY TESTING RESULTS					
Test	Grade	Material	Result	Date	NOTES
	Α				
L.A. ABRASION (MTM 102)	В	6A	12	7/26/2023	LA Abrasion results expire 5 years from reported date for this source
	С				
	D				
	E				
	F				
FREEZE-THAW TESTING (MTM 113, 114, 115)	Expansion		-0.001	12/08/2023	6A tested, expires 12/07/2028 The 6 series for FT is the standard and covers ALL gradations, while the 17 series result is
	Crush		69		
	SG (OD)		2.74		valid for 17 series gradations only
	Deleterious		as tested (soft 0		0.5%, sum of deleterious 0.5%)
A.W.I. (MTM 112)	Petrographic AWI				Contact Aggregate Quality
ADDRESS		LAST PRODUCER ON RECORD			

161 Peachey Street, Thessalon, ON, Canada POR 1L0

Holcim

Revised: Monday, December 11, 2023

95-013 Historical

NOTE: If you have updates for this pit (ex. Status, producer, or an increase in area for legal description) please contact Aggregate Quality Control